



## LUBRIN® HL ISO-VG 150

HL ISO-VG 150 is optimum alloyed and has a good performance level and a wide range of applications within the whole industry working in variable temperature range from -32 to +260. It is characterized by good viscosity-temperature behavior, high aging stability and reliable corrosion protection. Effective additives provide even under extreme loads a best wear protection. The behavior against sealing materials is neutral.

### Recommended for:

DIN 51 524 / part 1 (HL)

Typical characteristics			
Data	Unit	Method	Value
Density at 15°C	Kg/L	D-4052	0,886
Viscosity at 40°C	mm <sup>2</sup> /s	D 445	150
Viscosity at 100°C	mm <sup>2</sup> /s	D 445	15
Viscosity index (VI)		D 2270	91
Flash point (COC)	°C	D 92	248
Pour point	°C	D 97	-20

The characteristics shown are typical of current production. This data cannot be constructed as a legally binding warranty or guarantee of certain product properties or of the suitability of the product for a specific application. LUBRIN products are continually improved. Therefore LUBRIN reserves the right to change all the technical data in this product information at any time without notice. All sales and deliveries shall be subject to our current General Terms and Conditions of Sale and Terms.

Art. No : G44014

Lubrin GmbH  
Lübecker Str. 7, 65760 Eschborn, Germany  
Tel: +49 6196-202 9550  
Website: [www.lubrin.co](http://www.lubrin.co)  
Email: [info@lubrin.co](mailto:info@lubrin.co)

**File No. M17414\_2014.05.23**  
**Name: HL ISO-VG 150**

**Page 1 of 1**